
maxeon











Engineered for Performance

- Smaller cells stay cooler when shaded, extending panel life³
- An advanced encapsulant minimizes degradation from environmental exposure
- Conductive adhesive defends against daily temperature swings
- Redundant cell connections create flexible paths for continuous electricity flow



PERFORMANCE 6 | 535-555

POWER RANGE: 535 - 555 W

The Performance 6 panel is engineered to meet the unique needs of solar power plants. Bifacial power generation and G12 (210mm) cell technology combine to maximize power density, while its framed glass/glass construction offers greater durability for extended panel life.

Backed by a comprehensive warranty and an estimated 35-year useful life,¹ Performance panels wrap conventional front contact cells with 35 years of materials, engineering and manufacturing expertise to mitigate the reliability challenges of Conventional Panel design.

Durability that Translates to More Energy

Engineered to stand up to environmental stresses such as shading, daily temperature swings and high humidity, the Performance 6 is a high power panel uniquely suited for power plant EPCs and developers looking to maximize energy production.

A Track Record of Innovation Leadership

Performance panels represent the most deployed shingled cell panel in the industry—innovation protected by a growing portfolio of patents worldwide.²



Deployed

Year 30 Warranted Power Output



Countries



85.0%

90+ Patents

A Better Product. A Better Warranty.

The Performance 6 panel is backed by a 12-year product and 30-year power warranty.

 Year 1 Minimum Warranted Power Output 	98.0%
Maximum Annual Degradation	0.45%


PERFORMANCE 6 POWER: 535 - 555 W

Electrical Data, Front STC Characteristics ⁴					
Model	SPR-P6-555-UPP	SPR-P6-550-UPP	SPR-P6-545-UPP	SPR-P6-540-UPP	SPR-P6-535-UPP
Nominal Power (Pnom) ⁴	555 W	550 W	545 W	540 W	535 W
Power Tolerance	+3/0%	+3/0%	+3/0%	+3/0%	+3/0%
Efficiency	21.3%	21.1%	20.9%	20.7%	20.6%
Rated Voltage (Vmpp)	40.0 V	39.7 V	39.5 V	39.3 V	39.0 V
Rated Current (Impp)	13.89 A	13.85 A	13.80 A	13.76 A	13.71 A
Open-Circuit Voltage (Voc)	47.3 V	47.1 V	46.9 V	46.7 V	46.5 V
Short-Circuit Current (Isc)	14.73 A	14.68 A	14.64 A	14.59 A	14.54 A
Maximum System Voltage			1500 V UL		
Maximum Series Fuse			25 A		
Power Temp. Coef.			−0.34% / °C		
Voltage Temp. Coef.			-0.28% / °C		
Current Temp. Coef.			0.06% / °C		

Bifacial Characteristics					
Bifaciality (φPmax)			70% +/-10%		
PmaxBiF05	583 W	578 W	572 W	567 W	562 W
IscBiF05	15.46 A	15.41 A	15.37 A	15.31 A	15.26 A
PmaxBiF10	611 W	605 W	600 W	594 W	589 W
IscBiF10	16.20 A	16.14 A	16.10 A	16.04 A	15.99 A
PmaxBiF20	666 W	660 W	654 W	648 W	642 W
IscBiF20	17.67 A	17.61 A	17.56 A	17.50 A	17.44 A

Tests And Certifications (Pending)			
Standard Tests	UL 61730, UL 61215		
Quality Certs	ISO 9001:2015, ISO 14001:2015		
EHS Compliance	ISO 45001-2018, Recycling Scheme		
Ammonia Test	IEC 62716		
Desert Test	MIL-STD-810G		
Salt Spray Test	IEC 61701 (maximum severity)		
LeTID Test ⁵	IEC 61215 (MQT 23.1 LeTID detection) draft standard		
PID Test	IEC 62804		
Available Listings ⁶	UL		

Operating Condition And Mechanical Data		
Temperature	-40°F to +185°F (-40°C to +85°C)	
Impact Resistance	1 inch (25 mm) diameter hail at 52 mph (23 m/s)	
Solar Cells Monocrystalline PERC		
Tempered Glass	ered Glass High-transmission tempered anti-reflective	
Junction Box	IP-68, Evo2, 3 bypass diodes	
Weight	71.4 lbs (32.4 kg)	
Max. Load	Wind: 50 psf, 2400 Pa, 244 kg/m² back	
	Snow: 112 psf, 5400 Pa, 550 kg/m² front	
Frame	Class 2 silver anodized	



Please read the safety and installation guide.

- 1 Performance panels expected useful life of 35 years. Source: "P-Series Technology Technical Review," Leidos Independent Engineer Report. 2016. 2 Osborne. "SunPower supplying P-Series modules to a 125MW NextEra project." PV-Tech.org. March 2017.
- 3 Performance Series Thermal Performance, Z.Campeau 2016.
- 4 Measured at Standard Test Conditions (STC): irradiance of 1000 W/m², AM 1.5, and cell temperature 25° C.
- $5\,$ Fraunhofer CSP LID Sensitivity according to IEC 61215 (MQT 23.1 LeTID detection), 0.5% power loss at 700 hours.
- 6. Cert only covers front side performance.

Designed in the U.S.A. Assembled in Mexico

Specifications included in this datasheet are subject to change without notice.

© 2022 Maxeon Solar Technologies, Ltd. All Rights Reserved. View warranty, patent and trademark information at maxeon.com/legal.

